



SYNTITEC PP FILM 180

matt 3900, 180 µm

Universal matt-finish polypropylene film for indoor and outdoor displays and A-boards

In combination with aqueous ink systems, this tear resistant PP film is suitable for the production of A-boards, information stands and other POS applications. The matt paper like surface prevents reflections and delivers brilliant prints. Thanks to a thickness of 180 μm , the material provides high stiffness, easy handling and optimum processing characteristics. For example, it can be mounted without problems with double-sided adhesive tape. In combination with pigment inks, the material is suitable for short or mid-term outdoor applications.

Advantages

- Brilliant colour reproduction
- Splashproof prints for short- to medium-term outdoor applications
- Tear resistant
- · Quick further processing
- High scratch resistance
- PVC free

General tips

The converting and storage should take place in a climate from 35 to 65% to relative humidity at a temperature from 10 to 30°C. Keep the product in the original packaging (cardboard box and PE bag). It is always recommended that cotton gloves be used when handling InkJet coated materials to avoid fingerprints.

This product is excellent for both in and out-door application. For optimal outdoor applications the film must be printed with pigmented inks however this leaves a limited water-resistance. Therefore unlaminated media can only be used outside on a short-term basis. For example a print made on HP DJ2500 CP using UV pigment inks, gave a Q_U_V test result of approx 500 hrs, outdoor tests in Switzerland showed good results after 2 months (unlaminated) using ghe same inks (and 4 months with laminated prints). This product has excellent lamination properties, good results can be achieved with most hot and cold laminates. However when using hot laminates it is important that temperatures are not too hot (max 100°C) to avoid warping and ripples.

Physical data

Name	Value	Norm
Thickness (film) [µm]	180	ISO 4593
Weight [g/m²]	130	ISO 536
Whiteness, CIE D65/2°	102	ISO 11476
Shrinkage MD (5 min/120°C) [%]	~0.6	DIN 53377
Shrinkage CD (5 min/120°C) [%]	~0.05	DIN 53377

Technologies



Properties



19.04.2024 Page 1/1